# Monte Carlo Design and Experiments on the Neutron Shielding Performances of B<sub>2</sub>O<sub>3</sub>-ZnO-Bi<sub>2</sub>O<sub>3</sub> Glass System<sup>1</sup>

J. Kaewkhao<sup>a</sup>, T. Korkut<sup>b</sup>, \*, H. Korkut<sup>b</sup>, B. Aygün<sup>c</sup>, P. Yasaka<sup>a</sup>, S. Tuscharoen<sup>a</sup>, S. Insiripong<sup>d</sup>, and A. Karabulut<sup>c</sup>

<sup>a</sup> Center of Excellence in Glass Technology and Materials Science (CEGM), Nakhon Pathom Rajabhat University, Nakhon Pathom, 73000 Thailand

<sup>b</sup> Faculty of Engineering, Department of Nuclear Energy Engineering, Sinop, 57000 Turkey

<sup>c</sup> Faculty of Science, Department of Physics, Atatürk University, Erzurum, Turkey

<sup>d</sup> Physics Program, Faculty of Science and Technology, Muban Chombueng Rajabhat University, Ratchaburi, 70150 Thailand

\*e-mail: turgaykorkut@hotmail.com

Received December 11, 2015

Abstract—Neutron shielding properties of  $(90 - x)B_2O_3$ -10ZnO- $xBi_2O_3$  glass systems (where x = 15, 20, 25 and 30 mol %) were investigated by Monte Carlo simulations (FLUKA and GEANT4) and experiments. Neutron mass removal cross sections, number of inelastic scattering, elastic scattering, and capture interactions were estimated by simulations. <sup>241</sup>Am/Be neutron source was used for the neutron equivalent dose rate measurements. As a result, produced glass samples have fine neutron shielding capacity.

Keywords: Neutron shielding, bismuth-zinc-borate glass, Monte Carlo simulation DOI: 10.1134/S1087659617060050

#### INTRODUCTION

Glass materials are widely used in many industries. So, investigations of radiation shielding properties of glass materials are a coveted issue nowadays. Bismuth borate glasses are technologically important materials because of their high densities, low melting temperatures, excellent optical properties and high attenuation coefficients for X-ray and gamma rays. In addition to these fine properties, neutron shielding performances of these glass systems are an important issue.

There are several studies on bismuth borate and bismuth borosilicate glasses about their production techniques, optical properties and gamma radiation shielding capacities. In [1] bismuth-alumina-borosilicate glasses are produced using melt quenching technique and performed MAS-NMR spectroscopic measurements with thermal analysis [1]. Absorption spectroscopic studies on gamma irradiated bismuth borosilicate glasses were made and the effect of the heavy metal oxide Bi<sub>2</sub>O<sub>3</sub> on the glass composition was also studied [2]. In another study, the composition of the glass is (mol %)  $20Bi_2O_3 - 15Na_2O - 50B_2O_3 -$ 15SiO<sub>2</sub> was prepared by conventional melt quench method and effect of heavy ion irradiation on the structural properties of this glass system was studied. A significant decrease in the band gap is observed after irradiation which is indicative of the fact that radiation has caused compaction in the glass structure [3]. The ultrasonic velocity for different compositions of irradiated recycled heavy metal oxide (HMO) borosilicate glasses of the  $xBi_2O_3$ -50BaO-(50 -  $x)B_2O_3$  glass system (where x = 0, 5, 10, 15, 20 mol %) were studied by using the pulse echo technique [4]. The influence of gamma-ray irradiation on the optical properties of Bi<sub>2</sub>O<sub>3</sub>-B<sub>2</sub>O<sub>3</sub>-SiO<sub>2</sub> glass system was studied in another paper. Broadband infrared (IR) emission at 1310 nm with a FWHM over 200 nm is observed in the gammaray irradiated glass [5]. Radiation shielding parameters of bismuth borosilicate glass from 1 keV to 100 GeV were studied. Gamma rays shielding properties of (50 - x) SiO<sub>2</sub> : 15B<sub>2</sub>O<sub>3</sub> : 2Al<sub>2</sub>O<sub>3</sub> : 10CaO : 23Na<sub>2</sub>O :  $xBi_2O_3$  glasses (where x = 0, 5, 10, 15 and 20 mol %) were evaluated by using XCOM software [6]. Calculation study of radiation shielding capacities of silicate and borate heavy metal oxide glasses were made [7].

In this paper, neutron shielding properties of  $Bi_2O_3$ -ZnO- $B_2O_3$  glasses were studied. GEANT4 and FLUKA Monte Carlo codes were used to estimate shielding parameters. Neutron equivalent dose rate measurements were performed to determine shielding performances of produced samples. Results were compared to ordinary glass at the same dimension with the produced glass samples.

<sup>&</sup>lt;sup>1</sup> The article is published in the original.

KAEWKHAO et al.

B65Z10Bi25

B60Z10Bi30

Comparision of along complex mol %	Code
Composition of glass samples, mor 70	
$75B_2O_3 - 10ZnO - 15Bi_2O_3$	B75Z10Bi15
70B <sub>2</sub> O <sub>3</sub> -10ZnO-20Bi <sub>2</sub> O <sub>3</sub>	B70Z10Bi20

#### Table 1. Codes of produced glass samples

 $65B_2O_3 - 10ZnO - 25Bi_2O_3$ 

60B2O3-10ZnO-30Bi2O3

## Monte Carlo Codes

Monte Carlo is a method based on the random number seeds and the mathematical algorithms [8]. This technique can be applied for physical systems, especially in nuclear science. In this study we used FLUKA [9, 10] and GEANT4 [11, 12] as Monte Carlo simulators. FLUKA is a Monte Carlo package used in interactions between many subatomic particles and elements, compounds and mixtures. FLUKA has many advantages in terms of wide energy range. For example, it can simulate neutrons from thermal level to 20 TeV. Also it is useful in many scientific areas (high energy experimental physics and engineering, shielding, detector and telescope design, cosmic ray studies, dosimetry, medical physics and radio-biology). We used the FLUKA Monte Carlo code to simulate neutron and gamma radiation with different materials in our latest studies [13-17]. In some of these studies we compared FLUKA results to experiments. The FLUKA Monte Carlo Simulation code was used to calculate neutron mass removal cross sections of glass formulations. Detailed information can be found at its web page. GEANT4 is a toolkit for the simulation of the passage of particles through matter. Its areas of application include high energy, nuclear and accelerator physics, as well as studies in medical and space science. It has two hadronic interaction models such as the Quark-Gluon String Precompound (QGSP), the Bertini Model and the FRITIOF



Fig. 1. Experimental design for neutron equivalent dose rate measurements.

Precompound (FTFP). In the present study 4.9.4.p01 released version with QGSP-HP model was used to simulate interactions between neutrons and glass samples. GEANT4 Monte Carlo Simulation toolkit was used to obtain neutron mass removal cross sections and neutron scattering-capture information. Detailed information about GEANT4 can be found at web page.

#### Fabrication of Glass Samples

The glasses with their chemical compositions  $(90 - x)B_2O_3-10ZnO-xBi_2O_3$  (where x = 15, 20, 25 and 30 mol %) were prepared by the normal meltquenching technique. All chemicals; ZnO,  $Bi_2O_3$  and  $B_2O_3$ , used in the present work were of high purity. For each batch composition, 20 g of homogeneous mixture of starting chemicals were melted in high purity alumina crucibles by an electric furnace at a temperature of 1100°C for 3 hours. The melts were quenched by pouring into pre-heated stainless steel molds. The glasses were then annealed at 500°C for about 3 hours to remove thermal strains. Produced samples and their codes can be seen in Table 1.

#### Neutron Equivalent Dose Rate Measurements

For neutron equivalent dose rate measurement, we used a <sup>241</sup>Am-Be neutron source and a Canberra portable neutron detector equipment. <sup>241</sup>Am/Be source emits 2–11 MeV neutrons. The physical form of <sup>241</sup>Am/Be neutron source is a compacted mixture of AmO<sub>2</sub> with beryllium metal. The NP-100B detector provides us to detect slow and fast neutrons. Equivalent dose rates of the neutron field can be measured by it as  $\mu$ Sv per hour. Equivalent dose rate results were read via the RADACS software on the system PC. Experimental design is shown in Fig. 1.

#### **RESULTS AND DISCUSSION**

# **Results of Monte Carlo Simulations**

We calculated four different parameters by Monte Carlo simulations for four glass compositions. Neutron mass removal cross sections  $(\Sigma/\rho)$  simulated by FLUKA and GEANT4 codes can be seen in Fig. 2. As can be seen in this figure neutron mass removal cross sections decrease with decreasing  $B_2O_3$  contents. Looking at the R-square values, simulation results are around the mean values ( $R^2 = 0.99978$  for FLUKA and  $R^2 = 0.99934$  for GEANT4). Also FLUKA and GEANT4 results are compatible. Table 2 shows the distribution of neutrons as number of inelastic scattered, elastic scattered, captured and transported neutrons after neutrons-glass interactions. In other words, this table shows partitions of 1000000 primary neutrons after neutron-glass interactions. Number of inelastic and elastic scattered neutrons increased with decreasing B<sub>2</sub>O<sub>3</sub> percentage. Number of transported



Fig. 2. Neutron mass removal cross sections by Monte Carlo.

neutrons decreased with decreasing  $B_2O_3$  content. B70Z10Bi20 sample has the highest number of captured neutrons value.

# Results of Neutron Equivalent Dose Rate Measurements

Neutron equivalent dose rate measurements were performed for four glass samples and an ordinary glass sample which has the same dimensions with others. Figures 3 and 4, show equivalent dose rate values against number of count for this glass system and ordinary glass. For normal glass sample, equivalent dose rate values are varies between 0.46 and 1.27 uSv/h. Maximum and minimum equivalent dose rate values for B75Z10Bi15 are 0.55 and 0.73  $\mu$ Sv/h respectively. Other three glasses have equivalent dose rate values in the range of 1.18 and 0.27  $\mu$ Sv/h. Average dose rate values can be seen in Fig. 5. Looking at this figure, neutron shielding capacities of our samples are higher than ordinary glass sample. Also B75Z10Bi15 is the best neutron shielding glass with 36% difference from ordinary glass sample.

Looking at the results, it seems that there is a harmony between experimental and Monte Carlo results. As the  $B_2O_3$  content increased in the sample, the experimental equivalent dose rate (absorbed by detector) values decreased (Fig. 3) and the mass removal



Fig. 3. Equivalent dose rates for glass samples.

coefficient values, obtained by simulations (Fig. 2), increased. These results support the increase in the number of elastic and inelastic scattered neutrons and the decrease in the number of transported neutrons estimated by Monte Carlo simulations (Table 2). The materials to which neutrons are scattered in high numbers are valuable in terms of neutron shielding quality. That means, neutron shielding performance has increased with increasing  $B_2O_3$  content.

# CONCLUSIONS

In this paper, neutron interactions with  $(90 - x)B_2O_3 - 10ZnO - xBi_2O_3$  (where x = 15, 20, 25 and 30 mol %) glass system were modeled by FLUKA and GEANT4 Monte Carlo codes. Also neutron equivalent dose rate experiments were performed for produced four samples. The experimental and simulation results show that produced glasses including  $B_2O_3$ , ZnO, and  $Bi_2O_3$  have higher neutron shielding performance. B75Z10-Bi15 is the finest neutron shielding glass among others. Also neutron shielding performance increases with increasing  $B_2O_3$  content has increased. So, it can be said that produced glasses have fine compact neutron shielding glass systems in different nuclear applications.

	B75Z10Bi15	B70Z10Bi20	B65Z10Bi25	B60Z10Bi30
Inelastic(n, n')	19450	20996	22777	24750
Elastic(n, n)	179 398	186114	190107	194050
Capture	20	21	20	17
Transport	801132	792869	787096	781183
Total	1000000	1000000	1000000	1000000

 Table 2. Distribution of neutrons as number of inelastic scattered, elastic scattered, captured and transported neutrons after neutrons-glass interactions

GLASS PHYSICS AND CHEMISTRY Vol. 43 No. 6 2017



Fig. 4. Equivalent dose rates for ordinary glass.



Fig. 5. Average equivalent dose rates for samples.

#### REFERENCES

- Khanna, A., Saini, A., Chen, B., Gonzalez, F., and Pesquera, C., Structural study of bismuth borosilicate, aluminoborate and aluminoborosilicate glasses by <sup>11</sup>B and <sup>27</sup>Al MAS NMR spectroscopy and thermal analysis, J. Non-Cryst. Solids, 2013, vol. 373, p. 34.
- Kaur, R., Singh, S., and Pandey, O.P., Absorption spectroscopic studies on gamma irradiated bismuth borosilicate glasses, *J. Mol. Struct.*, 2013, vol. 1049, p. 386.
- Kaur, R., Singh, S., and Pandey, O.P., Modifications induced in the structural and optical properties of bismuth sodium borosilicate glass thin films by 120 MeV Ag7<sup>+</sup> ions, *Nucl. Instrum. Methods Phys. Rev. B*, 2013, vol. 305, p. 51.

- Bootjomchai, C., Laopaiboon, J., Nontachat, S., Tipparach, U., and Laopaiboon, R., Structural investigation of borosilicate recycled-barium-bismuth glasses under the influence of gamma-irradiation through ultrasonic and FTIR studies, *Nucl. Eng. Des.*, 2012, vol. 248, p. 28.
- Shen, W., Ren, J., Baccaro, S., and Cemmi, A., Broadband infrared luminescence in γ-ray irradiated bismuth borosilicate glasses, *Opt. Lett.*, 2013, vol. 38, no. 4, p. 516.
- 6. Chanthima, N. and Kaewkhao, J., Investigation on radiation shielding parameters of bismuth borosilicate glass from 1 keV to 100 GeV, *Ann. Nucl. Energy*, 2013, vol. 55, p. 23.
- 7. Singh, V.P. and Badiger, N.M., Shielding efficiency of lead borate and nickel borate glasses for gamma rays and neutrons, *Glass Phys. Chem.*, 2015, vol. 41, no. 3, p. 276.
- Ramírez-López, A., Soto-Cortés, G., González-Trejo, J., and Muñoz-Negrón, D., Computational algorithms for simulating the grain structure formed on steel billets using cellular automaton and chaos theories, *Int. J. Min. Metal. Mater.*, 2011, vol. 18, no. 1, p. 24.
- Ferrari, A., Sala, P.R., Fassò, A., and Ranft, J., FLUKA: a multi-particle transport code, CERN-2005-10, INFN/TC-05/11, SLAC-R-773, 2005.
- Battistoni, G., Muraro, S., Sala, P.R., Cerutti, F., Ferrari, A., Roesler, S., Fassò, A., and Ranft, J., The FLUKA code: description and benchmarking, in *Proceedings of the Hadronic Shower Simulation Workshop*, *AIP Conf. Proc.*, 2006, vol. 896, p. 31.
- Agostinelli, S. et al., GEANT4 a simulation toolkit, Nucl. Instrum. Methods Phys. Res. A, 2003, vol. 506, p. 250.
- Allison, J. et al., Geant4 developments and applications, *IEEE Trans. Nucl. Sci.*, 2006, vol. 53, p. 270.
- Korkut, T., Karabulut, A., Budak, G., and Korkut, H., Investigation of fast neutron shielding characteristics depending on boron percentages of MgB<sub>2</sub>, NaBH<sub>4</sub> and KBH<sub>4</sub>, J. Radioanal. Nucl. Chem., 2010, vol. 286. p. 61.
- Korkut, T., Korkut, H., Karabulut, A., and Budak, G., A new radiation shielding material: amethyst ore, *Ann. Nucl. Energy*, 2011, vol. 38, no. 1, p. 56.
- Korkut, T., Karabulut, A., Budak, G., Aygun, B., Gencel, O., and Hancerliogullari, A., Investigation of neutron shielding properties depending on number of boron atoms for colemanite, ulexite and tincal ores by experiments and FLUKA Monte Carlo simulations, *Appl. Radiat. Isotopes*, 2012, vol. 70, p. 341.
- Korkut, T., FLUKA Monte Carlo simulations about cosmic rays interactions with Kaidun meteorite, Adv. High Energy Phys., 2013, vol. 2013, ID826730.
- Korkut, T. and Korkut, H., Comparison of radiation damage parameter values for the widely used semiconductor gamma detector materials in wide energy range, *Radiat. Phys. Chem.*, 2014, vol. 97, p. 337.